

(12)特許協力条約に基づいて公開された国際出願

(19)世界知的所有権機関  
国際事務局



(43)国際公開日  
2005年2月17日 (17.02.2005)

PCT


(10)国際公開番号  
WO 2005/014420 A1

- (51) 国際特許分類: B65D 63/10, B29C 59/04
- (21) 国際出願番号: PCT/JP2004/011523
- (22) 国際出願日: 2004年8月4日 (04.08.2004)
- (25) 国際出願の言語: 日本語
- (26) 国際公開の言語: 日本語
- (30) 優先権データ:  
特願2003-290721 2003年8月8日 (08.08.2003) JP
- (71) 出願人(米国を除く全ての指定国について): 積水樹脂株式会社 (SEKISUI JUSHI KABUSHIKI KAISHA) [JP/JP]; 〒5300047 大阪府大阪市北区西天満2丁目4番4号 Osaka (JP).
- (72) 発明者; および
- (75) 発明者/出願人(米国についてのみ): 田近悟 (TAJIIKA, Satoru) [JP/JP]; 〒5300047 大阪府大阪市北区西天満2丁目4番4号 積水樹脂株式会社内 Osaka (JP). 山根進 (YAMANE, Susumu) [JP/JP]; 〒5300047 大阪府大阪
- (74) 代理人: 倉内義朗 (KURAUCHI, Giro); 〒5300047 大阪府大阪市北区西天満4丁目14番3号住友生命御堂筋ビル Osaka (JP).
- (81) 指定国(表示のない限り、全ての種類の国内保護が可能): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) 指定国(表示のない限り、全ての種類の広域保護が可能): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), ユーラシア (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), ヨーロッパ (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE,

[続葉有]

(54) Title: THERMOPLASTIC SYNTHETIC RESIN BAND AND METHOD FOR PRODUCING THE SAME

(54)発明の名称: 熱可塑性合成樹脂バンドおよびその製造方法



(57) Abstract: A method for producing a thermoplastic synthetic resin band (1) is disclosed wherein the front and back surfaces of a thermoplastic synthetic resin base (10) are provided with a number of mutually obliquely crossing parallel ridges (1a) of a given width and a number of diamond-shaped recesses (1b) having a given area defined by the parallel ridges (1a) by passing the thermoplastic synthetic resin base (10) between a pair of embossing rolls (2, 2) whose peripheral surfaces are provided with mutually obliquely crossing parallel grooves (2a) of a given width and a number of diamond-shaped raised sections (2b) defined by the parallel grooves (2a). In this connection, there are used such embossing rolls (2, 2) wherein the grooves (2a) are so formed as to have a peripheral crossing angle of 15-30 degrees without changing the width of the grooves (2a) or the area of the raised sections (2b). With this method, there can be obtained a thermoplastic synthetic resin band (1) in which the longitudinal crossing angle (a) of the ridges (1a) is 15-30 degrees.

(57) 要約: 本発明の熱可塑性合成樹脂バンドの製造方法は、互いに斜交する一定幅の平行凹溝2aと、この平行凹溝2aによって区画されるダイヤ形状の多数の凸部2bとが外周面に形成された一对のエンボスロール2、2間

WO 2005/014420 A1

に、熱可塑性合成樹脂基材10を通過させ、この熱可塑性合成樹脂基材10の表裏面に、互いに斜交する一定幅の多数の平行凸条1aと、この平行凸条1aによって一定面積に区画されたダイヤ形状の多数の凹部1bとを形成する熱可塑性合成樹脂バンド1の製造方法である。凹溝2aの幅や凸部2bの面積を変更することなく、凹溝2aの周方向の交差角度のみを15~30度としたエンボスロール2、2を用いる。この製造方法によって凸条1aの長手方向の交差角度aが15~30度となされた熱可塑性合成樹脂バンド1が得られる。



IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

2文字コード及び他の略語については、定期発行される各PCTガゼットの巻頭に掲載されている「コードと略語のガイダンスノート」を参照。

添付公開書類:

— 国際調査報告書